


SWATCHBOOK: GamColor
COLOR FILTER: 355 Amber Flame
DESCRIPTION: Color Effects Lighting Filter.
TRANSMISSION = Y 51% or stop loss
MIRE D SHIFT = Not Applicable.
CC EQUIVALENT = Not Applicable.

COLORIMETRIC DATA

OBSERVER: CIE 1964 10°
SOURCE:

- 'A' (tungsten)
- 'D65' (daylight)

R: 255
G: 140.2
B: 0




| HUNTER LAB SOURCE A | |
|---------------------|---------|
| L* | 76.376 |
| A* | 41.108 |
| B* | 118.242 |

| HUNTER LAB SOURCE D65 | |
|-----------------------|----------|
| L* | 68.25968 |
| A* | 43.1697 |
| B* | 105.4362 |

| CIE 1964 10° SOURCE A | |
|-----------------------|--------|
| Y | 50.502 |
| (x) | 0.597 |
| (y) | 0.400 |

| CIE 1964 10° SOURCE D65 | |
|-------------------------|--------|
| Y | 38.325 |
| (x) | 0.565 |
| (y) | 0.426 |



| nm. | 360 | 380 | 400 | 420 | 440 | 460 | 480 | 500 | 520 | 540 | 560 | 580 | 600 | 620 | 640 | 660 | 680 | 700 | 720 | 740 |
|---------|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| trans % | NA | 26 | 5 | 1 | 1 | 0 | 1 | 1 | 2 | 27 | 42 | 68 | 82 | 84 | 84 | 85 | 85 | 85 | 86 | 86 |

MATERIAL SPECIFICATIONS:

General Description: Deep-Dyed Polyester
Substrate: Polyester
Thickness: 2.0 mil (.002" or 50 micron)

Manufactured in: U.S.A.

AVAILABLE SIZES:

- √ 20 in. x 24 in. sheets (50cm x 60cm)
 - √ 21 in. x 24 in. sheets (53 x 60cm)
 - √ 24 in. x 25 ft. rolls (60cm x 7.62m)
 - √ 24 in. x 50 ft. (60cm x 15.24m)
 - √ 24 in. x 198 in. (60cm x 5m)
 - √ 48 in. x 25 ft. rolls (121cm x 7.62m)
 - √ 60 in. x 20 ft. rolls (152.4cm x 6.10m)
- Consult Rosco