


SWATCHBOOK: ROSCOLUX
COLOR FILTER: #36 MED PINK
DESCRIPTION: Color Effects Lighting Filter.
TRANSMISSION = 46% or -1.1 stop loss
MIREL SHIFT = Not Applicable.
CC EQUIVALENT = Not Applicable.

COLORIMETRIC DATA

OBSERVER: CIE 1964 10°
SOURCE:

- 'A' (tungsten)
- 'D65' (daylight)




| HUNTER LAB SOURCE A | |
|---------------------|--------|
| L* | 75.911 |
| A* | 36.127 |
| B* | 0.078 |

| HUNTER LAB SOURCE D65 | |
|-----------------------|--------|
| L* | 71.815 |
| A* | 39.83 |
| B* | -9.692 |

| CIE 1964 SOURCE A | |
|-------------------|--------|
| Y | 49.743 |
| (x) | 0.511 |
| (y) | 0.361 |

| CIE 1964 SOURCE D65 | |
|---------------------|--------|
| Y | 43.384 |
| (x) | 0.367 |
| (y) | 0.278 |



| | | | | | | | | | | | | | | | | | | | | |
|---------|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|-----|
| nm. | 360 | 380 | 400 | 420 | 440 | 460 | 480 | 500 | 520 | 540 | 560 | 580 | 600 | 620 | 640 | 660 | 680 | 700 | 720 | 740 |
| trans % | 38 | 56 | 69 | 67 | 59 | 48 | 38 | 30 | 26 | 27 | 34 | 52 | 71 | 82 | 85 | 86 | 86 | 86 | 86 | 87 |

MATERIAL SPECIFICATIONS:

General Description: Co-extruded Polycarbonate Film
Substrate: PC (Polycarbonate)
Thickness: 3.0 mil (.003" or 76.2 micron)

Manufactured in: U.S.A.

AVAILABLE SIZES:

- √ 20 in. x 24 in. sheets (50cm x 60cm)
- √ 24 in. x 25 ft. rolls (60cm x 7.62m)
- 48 in. x 25 ft. rolls (121cm x 7.62m)
- 60 in. x 20 ft. rolls (152.4cm x 6.10m)
- 13.5 in. Diameter Glass (34.3cm) - Cut to order